



Polyester Ripcord

Type: Polyester Ripcord

Composition: 100% Polyester

Application: Use for the stripping of various cables

Property	Unit	Technical Standard
Denier	D	2000
Liner Density	m/kg	4500
Tensile Strength	N	≥160
Elongation at Break	% (min)	≥15
Twist	m	80
Colour		Red
Shrinkage	% (180 °C, 2min)	≤5

Packaging

ID (mm) : 94

The data presented herein is given in good faith and correct to the best of our knowledge at publication. Values quoted are typical and do not constitute a guarantee of performance and UNIGEL SIBER reserve the right to make alterations without notice. UNIGEL SIBER is a registered trademark

UNIGEL SIBER Inc.
1027 19th Street S.W
Hickory,
NC 28602
United States of America